

WHAT IS CLAIMED IS:

*del*  
*A)*

1. A method for forming a crystalline silicon nitride layer, comprising the steps of:

providing a crystalline silicon substrate with an  
5 exposed surface;

precleaning the exposed surface by employing a  
hydrogen prebake; and

exposing the exposed surface to nitrogen to form a  
crystalline silicon nitride layer.

10 2. The method as recited in claim 1, wherein the  
step of precleaning includes the step of employing a  
hydrogen fluoride wet clean process to remove native  
oxide from the exposed surface.

15 3. The method as recited in claim 2, wherein the  
step of precleaning the exposed surface by employing a  
hydrogen prebake is delayed from the step of employing a  
hydrogen fluoride wet clean process to remove native  
20 oxide from the exposed surface by an interval of between  
about 30 seconds and about 3600 seconds.

25 4. The method as recited in claim 1, wherein the  
step of precleaning includes the step of prebaking the  
exposed surface in the presence of hydrogen gas at a  
temperature between about 400 °C and about 1300 °C.

5. The method as recited in claim 1, wherein the step of precleaning includes the step of prebaking the exposed surface in the presence of hydrogen gas at a pressure between about  $10^{-9}$  Torr and about 600 Torr.

5

6. The method as recited in claim 1, wherein the nitrogen includes at least one of nitrogen gas, ammonia, atomic nitrogen plasma, an organic nitrogen precursor and an inorganic nitrogen precursor.

10

7. The method as recited in claim 1, wherein the step of exposing the exposed surface to nitrogen to form a crystalline silicon nitride layer includes the step of introducing ammonia at a temperature of between about 400 °C and about 1300 °C.

15

8. The method as recited in claim 1, wherein the step of exposing the exposed surface to nitrogen to form a crystalline silicon nitride layer includes the step of maintaining ammonia at a pressure of between about  $10^{-6}$  Torr and about one atmosphere.

20

9. A semiconductor device fabricated in accordance with the method as recited in claim 1.

25

10. A method for forming a node dielectric layer in

*See  
A2*

deep trenches, comprising the steps of:

providing a crystalline silicon substrate with trenches formed therein, the trenches including exposed silicon surfaces;

5        precleaning the exposed surfaces by employing a hydrogen prebake;

      exposing the exposed surfaces to ammonia to form a crystalline silicon nitride layer;

10        depositing an amorphous silicon nitride layer over the crystalline silicon nitride layer; and

      oxidizing the amorphous silicon nitride layer to form a node dielectric layer.

15        11. The method as recited in claim 10, further comprising the step of employing a hydrogen fluoride clean process to remove native oxide from the exposed surfaces.

20        12. The method as recited in claim 11, wherein the step of precleaning the exposed surfaces by employing a hydrogen prebake is delayed from the step of employing a hydrogen fluoride clean process to remove native oxide from the exposed surfaces by an interval of between about 30 seconds and about 3600 seconds.

25        13. The method as recited in claim 10, wherein the step of precleaning includes the step of prebaking the

*Cancel  
A2*

100  
99  
98  
97  
96  
95  
94  
93  
92  
91  
90  
89  
88  
87  
86  
85  
84  
83  
82  
81  
80  
79  
78  
77  
76  
75  
74  
73  
72  
71  
70  
69  
68  
67  
66  
65  
64  
63  
62  
61  
60  
59  
58  
57  
56  
55  
54  
53  
52  
51  
50  
49  
48  
47  
46  
45  
44  
43  
42  
41  
40  
39  
38  
37  
36  
35  
34  
33  
32  
31  
30  
29  
28  
27  
26  
25  
24  
23  
22  
21  
20  
19  
18  
17  
16  
15  
14  
13  
12  
11  
10  
9  
8  
7  
6  
5  
4  
3  
2  
1

exposed surfaces in the presence of hydrogen gas at a temperature between about 400 °C and about 1300 °C.

14. The method as recited in claim 10, wherein the  
5 step of precleaning includes the step of prebaking the exposed surfaces in the presence of hydrogen gas at a pressure between about  $10^{-9}$  Torr and about 600 Torr.

15. The method as recited in claim 10, wherein the  
10 step of exposing the exposed surfaces to ammonia to form a crystalline silicon nitride layer includes the step of introducing the ammonia at a temperature of between 400 °C and about 1300 °C.

15. The method as recited in claim 10, wherein the  
step of exposing the exposed surfaces to ammonia to form a crystalline silicon nitride layer includes the step of maintaining the ammonia at a pressure of between about  $10^{-6}$  Torr and about one atmosphere.

20

17. A semiconductor device fabricated in accordance with the method as recited in claim 10.

18. A trench capacitor comprising:  
25 a crystalline silicon substrate including deep trenches having surfaces in the substrate substantially

free of native oxide; and

a dielectric stack, including a crystalline silicon nitride layer, formed on the surfaces of the trenches, the dielectric stack for forming a node  
5 dielectric between electrodes of the trench capacitor.

19. The trench capacitor as recited in claim 18, wherein the crystalline silicon nitride layer includes a thickness of between about 3 Å and about 40 Å.

10

20. The trench capacitor as recited in claim 18, wherein the dielectric stack includes an oxidized amorphous nitride layer.

15

*add  
A3*